



# BLUE OX 901

## POLYURETHANE ADHESIVE SYSTEM

BLUE OX  
901

**BLUE OX™ 901** brings strength, reliability, and extreme durability in a very low odor polyurethane adhesive system. With a convenient 1:1 mix ratio by weight and volume, **BLUE OX™ 901** brings reliability to the assembly line. The low odor formulation makes **BLUE OX™ 901** the perfect adhesive for applications involving large bond lines in confined area's, as well as high volume production runs. The flexible high strength **BLUE OX™ 901** is the ideal replacement for high odor methacrylates, and eliminates the residual stink they leave behind. Whether your bonding fiberglass, aluminum, steel or plastic, **BLUE OX™ 901** delivers temperature and moisture resistant bonds in nice balance between positioning time and handling strength.

### PHYSICAL PROPERTIES

TEST	RESULT
Hardness, Shore A (after 30 minutes @ 25°C)	50
Hardness, Shore D (after 18 hours @ 25°C)	50
Hardness, Shore D (after 7 days @ 25°C)	60
Lap Shear Strength AL/AL acid etched	
24 hours @ 25°C	2150 psi
7 days @ 25°C	2780 psi
@-40°C	3750 psi
@82°C	450 psi

### TYPICAL PROPERTIES

	Part A	Part B	Mixed
Color	Beige	White	Off-White
Viscosity@25°C	20,000cps	20,000cps	20,000cps
Weight per Gallon	11.75lbs	11.75lbs	11.75lbs
Shelf life	6 months	6 months	-
Filler Type	Non-Abrasive	Non-Abrasive	Non-Abrasive
Gel Time (20gm mass 25°C)	-	-	4 min
Tack-Free Time (20gm mass 25°C)	-	-	30 min
<b>MIX RATIO</b>			
	Parts by Weight		Parts by Volume
BX901 Part A	1		1
BX901 Part B		1	1
FOR FULL STRENGTH ALLOW 7 DAYS AT 25°C (77°F)			

We believe the information contained herein is current and accurate as of this date of this Technical Data Sheet. Since the use of this information and these opinions and the conditions of use of this product are not under the control of ADHESIVE R&D®, Inc. or its agents or distributors, it is the user's obligation to determine the conditions of safe use of this product. The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. ADHESIVE R&D®, Inc. warrants that the product conforms with ADHESIVE R&D®'s written specifications, and is free from defects and disclaims all other warranties, expressed or implied and is not responsible for loss claim of damages resulting from the use of its products.

Rev 01/03